

Streetscape[®] High-Strength Bedding Concrete

A superior quality polymer modified High-Strength Bedding Concrete, manufactured under an ISO 9001 quality controlled environment; using dried sands, lime, cement and additives specially designed to meet or exceed the requirements of BS 7533 part 7 & 12. The product is used for bedding natural stone flags, cobbles and setts, clay and concrete pavers in a rigid construction.

- Complies with BS 7533 part 7 & 12
- Long term durability
- Consistently high quality mix
- High early strengths
- Available in 25kg bags and site silos
- Eliminates waste and cleaner, safer sites



Working Instructions

High-Strength Bedding Concrete should be used in suitable bonded rigid constructions. The product should not be used in temperatures below 3° C in a falling temperature or below 2° C on a rising thermometer. The surface of the substrate should not be frozen or >25° C before bedding commences. Movement joints will be required in rigid/bonded constructions and should be designed and marked by the design team.

Substrate

The substrate, including sub-base and road base should meet the requirements of the relevant part of BS7533 depending on type of use. The substrate should then be pre-soaked and have all ponded water removed prior to application.

Preparation

All substrates must be suitable to receive the laying course as per current good working practices. All substrates for bonded constructions should be clean and thoroughly sound, free from oils, grease, dust, loose particles or any other contaminants which may interfere with adhesion.

Mixing

The product is mixed to the desired consistency either from a site silo and continuous mixer or in a suitable site mixer if 25kg bags are used. Add 2 - 2.5L of clean water per 25kg bag to achieve the desired semi-dry workability. Do not rewet previously mixed batches. Material mixed from bulk silos should be done so in accordance with the site training given by our technical team.

Priming

To achieve a bond strength as described in BS 7533, the substrate must be primed using Priming Slurry prior to placing High-Strength Bedding Concrete. All paving units must be primed with Priming Slurry promptly prior to placing into High-Strength Bedding Concrete.

Application

HSBC can be laid in depths of 10-75mm in one layer. Greater depths can be achieved using the layer on layer method. Place the product on the pre-soaked and freshly primed base and spread to the desired depth. Ensure to use the material while it is still moist and fresh. Prime the back of the paving unit and immediately place it in position, using a rubber mallet to bed and level. When applying another layer to a layer which has cured, it should first be primed with Priming Slurry. Place the product on the pre-soaked and freshly primed base and spread to the desired depth. The substrate must not be frozen. The product will take longer to gain strength during colder conditions.

Approx. Product Yield		
Bedding Depth	kgs of material req.	25kg bag per m ²
10	19	1
20	38	2
30	57	3
40	76	4
50	95	4
60	114	5
70	133	6
75	143	6

Streetscape® High-Strength Bedding Concrete

Storage

Bulk bags and packed products must be stored clear of the ground in cool, dry conditions and protected from wind, rain and external physical damage. Packed products must be stored in original unopened bags.

Disposal Considerations

Waste treatment methods: Alternative uses should be sought for any surplus mortar. Mortar waste should be disposed of in accordance with local authority guidance/regulations. Avoid entry of mortar waste into sewage or drainage systems or bodies of water, e.g. streams and rivers.

Safety

Classification according to Regulation (EC) No 1272/2008 CLP. Hazard pictograms: GHS05 corrosion. Signal Word: Danger. Hazard-determining components of labelling: Contains Portland Cement. All standard precautions for the handling of construction materials/chemicals must be taken. Get medical advice / attention IF YOU FEEL UNWELL. See Kilsaran Health and Safety Data Sheet for further detailed information.

Hazard Statements

- H315 - Causes skin irritation.
- H317 - May cause an allergic skin reaction.
- H318 - Causes serious eye damage.
- H335 - May cause respiratory irritation.

Precautionary Statements

- P102: Keep out of reach of children.
- P202: Do not use until all safety precautions have been read and understood.
- P260: Do not breathe dust/fume/gas/mist/vapours/spray
- P262: Do not get in eyes, on skin or on clothing.
- P280: Wear protective gloves / protective clothing / eye protection / face protection.
- P305+P351+P338+P310: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. Get medical advice / attention.
- P302+P352+P333+P313: IF ON SKIN: Wash with plenty of soap and water. If skin irritation or rash occurs get medical advice / attention.
- P362: Take off contaminated clothing
- P363: Wash contaminated clothing before reuse
- P403+P233 Store in well-ventilated place. Keep container tightly closed.
- P405: Store locked up.
- P501 Disposal: Allow to harden and dispose of as concrete waste.

Technical Information

Streetscape®: High-Strength Bedding Concrete	
Compressive Strength 28 days (BS EN 1015-11)	43 N/mm ²
Flexural Strength 28 days (BS EN 1015-11)	> 4.5 N/mm ²
Adhesion Strength (with Priming Slurry) (BS EN 1015-12)	> 2.0 N/mm ²
Shrinkage (BS EN 445)	< 0.1%
Density	1900 kg/m ³
Modulus Of Elasticity (DIN 18555-6)	16,000 N/mm ²
Maximum Thickness	75mm (applied in a single pass)
Minimum Thickness	10mm
Use (External Use)	Yes
Use (Internal Use)	Yes
Yield	See table opposite
Recommend water content	8 - 10%
Pot life	Maximum 60 mins depending on ambient conditions
Hardening Time (before foot traffic)	12 hours
Hardening Time (before vehicle traffic)	24 hours (depending on site conditions)



FOR MORE INFORMATION CONTACT: Smet Building Products Ltd

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 ROI: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie



Marketplace+