

Fliesenfest S1 turbo

S1 rapid-set flexible tile adhesive

FF 451



Extra-rapid-set, cementitious flexible tile adhesive, meeting C2 FT S1 requirements to DIN EN 12004, also for fully vitrified stoneware. Suitable for use in conjunction with wall and floor heating and Sopro waterproof membranes. Flexible, sag-resistant and with high crystalline water binding capacity.

- For walls and floors, indoors and outdoors
- C2: tensile adhesion strength $\geq 1.0 \text{ N/mm}^2$
- F: early tensile adhesion strength $> 0.5 \text{ N/mm}^2$ after 6 hours
- T: thixotropic – high sag resistance due to fibre reinforcement
- S1: deformability $\geq 2.5 \text{ mm}$
- Working life: approx. 20 minutes
- Walkable and groutable: after approx. 2 hours
- Low-chromate to Regulation (EC) No 1907/2006, Annex XVII

Coverage: Approx. $1.3 \text{ kg / m}^2 / \text{mm}$ dry coat thickness



| Order nr. | Delivery form | Pcs./pal. | kg/pal. |
|-----------|---------------|-----------|----------|
| 7745125 | Bag 25 kg | 40 | 1.000 kg |

Use With earthenware, stoneware and fully vitrified stoneware tiles, mosaic, discoloration-resistant natural stone units, ceramic split tiles and split tile fittings, clinker floor tiles and equivalent materials. For construction of ledges/shelves, lightweight internal walls, aerated concrete block facings to sanitary appliances (e.g. bathtubs) and the like. For full-surface installation of foam, cork, peat, wood-fibre etc. insulation board. For process water tanks, swimming pools, operating theatres, escape routes.

Properties Excellent contact adhesion, fresh adhesive sag resistance and high water retentivity, resistant to water and freeze-thaw cycles, high early strength.

Coat Thickness Max. 5mm in compacted adhesive bed

Substrate Preparation Substrate shall be clean, solid, strong, dimensionally stable and free from any adhesion-impairing substances. Fill any existing cracks in screed with structurally bonding Sopro SH 649 shaken resin. Level out any gross irregularities using Sopro RAM 3 454 renovation and levelling mortar or Sopro RS462 repair filler; for floors, use Sopro FS 15 550 floor-levelling compound, Sopro VS 582 self-levelling filler or Sopro FS 5 549 floor-levelling compound. Cement screeds shall be 28 days old and dry. Screeds incorporating Sopro Rapidur® B1 rapid-set screed binder are ready to receive tiles after only 12 hours, Sopro Rapidur® B3 after 1 - 2 days, and Sopro Rapidur® B5 after 3 days. (Self-levelling) calcium sulphate screeds (anhydrite screeds) shall be adequately ground, vacuum-cleaned and primed, and shall exhibit moisture content $\leq 0.5\%CM$ for unheated and $\leq 0.3\%CM$ for heated constructions. Gypsum plasterwork shall be dry, single-coat and shall not be felt-floated or smoothed. Cement and calcium sulphate screeds incorporating heating elements shall be heated up to ensure adequate drying out prior to flooring installation. Floating cement screeds or unbonded cement screeds on separating layer shall exhibit residual moisture $\leq 2.0\%CM$. Bonded cement screeds may be tiled as soon as they are walkable. When laying natural stone, risk of discoloration due to moisture penetration must be taken into account. All relevant standards, guidelines and recommendations shall apply; workmanship shall comply with good practice.

Primer For high- and variable-suction substrates: Sopro GD 749 primer and Sopro SG 602 primer-sealer

For non-absorbent substrates: Sopro HPS 673 bonding primer

For calcium sulphate screeds: Sopro MGR 637 multi-purpose primer (for all sizes), Sopro GD 749 primer (sizes up to 0.2 m²), Sopro SG 602 primer-sealer (sizes up to 1.0 m²)

For stabilizing friable mineral substrates and as adhesion promoter on smooth substrates: Sopro EPG 1522 epoxy primer

For further information, please consult relevant technical data sheets.

Application Mix Sopro FF 451 with water to homogeneous consistency. Apply contact layer, pressing down heavily, then apply combed bed with suitable notched trowel (tool angle 45° – 60°). Do not prepare an area of more than approx. 1.5 m². Press tiles firmly into bed, position and align before adhesive skins over. Rake out joints prior to hardening and wash down covering. Do not retemper stiffened mortar by addition of water or fresh material to restore workability. Pretreatment with Sopro MGR 637 multi-purpose primer or Sopro EPG 522 epoxy primer is required when laying large-format tiles with edge length exceeding 60 cm or of size exceeding 0.2 m² on calcium sulphate-based substrates.

| | | |
|---------------------|--------------------|--------------|
| Water demand | Per package | 25 kg |
| | Water requirement | 6,5 l - 7 l |

Walkable / Groutable After approx. 3 hours or after setting of adhesive; take measures to spread loads over floor

| Loadable | After approx. 1 day; in commercial facilities after approx. 2 days, in areas subject to high wet exposure after approx. 3 days, for underwater applications after approx. 10 days, in conjunction with wall and floor heating after approx. 14 days. | | | | | | | | | | | | | | | | | | | |
|---|--|-----|-----|-----|-----|----|----------------|---|---|---|----|----|----|----------------------------|-----|-----|-----|-----|-----|----|
| Suitable Substrates | Min. 3-month-old concrete, aerated concrete; cement and lime/cement render; renders made from masonry cement; plane, flush-jointed masonry (no composite masonry); paperless gypsum, gypsum plasterboard and gypsum fibreboard drywall panels; cement screeds; calcium sulphate screeds; board subfloors. As a basic requirement, all substrates shall, be solid, strong and dimensionally stable. Specifications of DIN 18157 shall be observed. | | | | | | | | | | | | | | | | | | | |
| GEV Emissioncode | EC1PLUS very low emissionPLUS | | | | | | | | | | | | | | | | | | | |
| Maturation time | 3 - 5 minutes | | | | | | | | | | | | | | | | | | | |
| Open Time | Approx. 20 minutes | | | | | | | | | | | | | | | | | | | |
| Underwater And Permanently Underwater Area | Suitable | | | | | | | | | | | | | | | | | | | |
| Application Temperature | From +5 °C to +25 °C (substrate, air, material) | | | | | | | | | | | | | | | | | | | |
| Working Life | Approx. 20 minutes | | | | | | | | | | | | | | | | | | | |
| Coverage Chart | <table border="1"> <thead> <tr> <th>Serration (mm)</th> <th>4</th> <th>6</th> <th>8</th> <th>10</th> <th>12</th> <th>20</th> </tr> </thead> <tbody> <tr> <td>Coverage kg/m²</td> <td>1.3</td> <td>2.0</td> <td>2.6</td> <td>3.3</td> <td>3.9</td> <td>--</td> </tr> </tbody> </table> <p>All stated consumption/coverage rates depend on angle of application with notched trowel and on substrate type and levelness. 20 mm serration corresponds to M1 serration to TKB (German Technical Committee for Construction Adhesives) guidance paper (U-shaped serration).</p> | | | | | | Serration (mm) | 4 | 6 | 8 | 10 | 12 | 20 | Coverage kg/m ² | 1.3 | 2.0 | 2.6 | 3.3 | 3.9 | -- |
| Serration (mm) | 4 | 6 | 8 | 10 | 12 | 20 | | | | | | | | | | | | | | |
| Coverage kg/m ² | 1.3 | 2.0 | 2.6 | 3.3 | 3.9 | -- | | | | | | | | | | | | | | |
| Recommendation for grouting | <p>The following are recommended for grouting ceramic tiles with absorbent tile bodies (earthenware) for stated joint widths:</p> <p>from 1 to 5 mm – Sopro Saphir® 5 water-repellent tile grout</p> <p>from 1 to 10 mm – Sopro DF 10 flexible designer tile grout</p> <p>The following are recommended for grouting tiles with low-suction or non-absorbent tile bodies (stoneware and fully vitrified stoneware) for stated joint widths:</p> <p>from 1 to 10 mm – Sopro DF 10 flexible designer tile grout</p> <p>from 2 to 20 mm – Sopro FL plus flexible tile grout</p> <p>The following are recommended for grouting natural and cast stone coverings for stated joint widths:</p> <p>from 1 to 10 mm – Sopro DF 10 flexible designer tile grout</p> <p>from 2 to 20 mm – Sopro FL plus flexible tile grout</p> <p>The following are recommended for grouting coverings subject to high mechanical loads (workshops, commercial facilities) for stated joint widths:</p> | | | | | | | | | | | | | | | | | | | |

from 1 to 10 mm – Sopro TF+ high-strength tile grout

from 3 to 30 mm – Sopro TFb high-strength tile grout

The following are recommended as chemical-resistant tile grouts for stated joint widths:

from 1 to 10 mm – Sopro DFX designer epoxy tile grout

from 1.5 to 12 mm – Sopro FEP epoxy tile grout

Wall and floor heating

Suitable

Tools

Mixing attachment, notched trowel with suitable serration: 3 – 4 mm for tesserae, 4 – 6 mm for wall and floor tiles, 6 – 10 mm for heavy ceramics.

Tool cleaning

Wash tools with water immediately after use

Test certificates

Available on request

Shelf Life

Approx. 6 months (in dry conditions, in original, unopened containers)

Giscode A

ZP1

CE Marking



Safety instructions

Labelling in accordance with Regulation (EC) No 1272/2008 (CLP).

GHS07

Signal word Attention

Causes serious eye irritation.

Keep out of reach of children.

Read label before use.

German Water Hazard Class: German Water Hazard Class WGK 1 (slightly hazardous to water)

GISCODE: ZP1

Low-chromate to Regulation (EC) No 1907/2006, Annex XVII

Please observe the current version of the product information, the currently valid declaration of performance under the EU Construction Products Regulation, and the latest version of the relevant safety data sheet to EC Regulation No 1907/2006, also available from the Internet at www.sopro.com! This document serves as a product description and sets out general details, based on empirical and test data, that take no account of specific cases of application. No liability may be construed and no claims shall be accepted in respect of these details. Should you require assistance, please contact our Technical Counselling Service.

Disposal

The generation of waste should be avoided or minimized wherever possible. Recover if possible. A waste code (EWC) according to European List of Waste (LoW) cannot be specified, due to dependence on the usage. Contact and send to an authorized waste disposal service.

Methods of disposal:

Disposal of this product, solutions, packaging and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.

Dispose of surplus and nonrecyclable products via a licensed waste disposal contractor.

Do not dispose of waste into sewers.

Hazardous waste: Yes

Disposal considerations:

Do not allow to enter drains or watercourses.

Dispose of product according to all federal, state and local applicable regulations.

If this product is mixed with other wastes, the original waste product code may no longer apply and the appropriate code should be assigned.

Dispose of containers contaminated by the product in accordance with local or national legal provisions. For further information, contact your local waste authority.

Special precautions:

This material and its container must be disposed of in a safe way. Care should be taken when handling untreated empty containers.

Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.

Empty containers or liners may retain some product residues. Do not re-use empty containers.

bringing european innovation

smet

FOR MORE INFORMATION CONTACT: **Smet Building Products Ltd**

93A Belfast Road | Newry | BT34 1QH | Northern Ireland

T: +44 (0)28 3026 6833 ROI: +353 (0) 1697 8586

E: info@smetbuildingproducts.com

smetbuildingproducts.com or smet.ie



The information, and, in particular, the recommendations relating to the application and end-use of SMET distributed products, are given in good faith based on SMET's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with the manufacturer's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.